



Type	Particle Size (nm)	Specific Surface Area(m <sup>2</sup> /g)	DBP Absorption (cc/100g)	Tinting Strength (%)	Blackness reflectivity (%)	pH	Volatile Matter (%)
YGB1355	20	320	90	138	28	2.5	8.0
YGB1405	25	240	70	130	35	2.5	8.0
YGC7705	22	160	60	130	38	8.0	1.5
YGC3305	30	85	70	110	48	7.5	1.0
YGC3105	28	105	113	113	42	7.5	1.5
YGC3106	28	100	108	108	45	7.5	1.0
YGC3705	28	88	121	100	50	8.0	1.8
YGC4725	50	28	65	95	55	7.0	1.0
YGGT-1	24	125	112	120	28	8.0	0.8
YGGT-2	24	125	71	122	26	7.5	0.8
YGGT-3	28	75	75	110	27	8.0	1.0
YGGT-5	24	130	65	125	26	7.2	0.4
YGGT-8	23	158	65	135	27	7.5	0.8
YGJAZ-1	25	116	116	120	28	7.4	0.6
YGJAZ-4	24	120	125	122	30	7.7	0.7
YG205	26	85	100	105	45	7.5	0.8
YG2	26	120	75	115	42	8.0	1.0
YGDJ-5	25	120	118	119	28	8.0	0.8

Remark: The above data is based on the local representative of sampling analysis, which is only for reference, not the Goods Identification.