



Type	Particle Size (nm)	Specific Surface Area (m ² /g)	DBP Absorption (cc/100g)	Tinting Strength (%)	Blackness reflectivity (%)	pH	Volatile Matter (%)	Recommend Application	
								High-grade finish coat	Coatings &Paints
YGB1000	12	560	98	150	12	2.0	18.0	●	
YGB1050	13	480	95	146	15	2.0	16.0	●	
YGB1100	13	520	105	152	14	2.5	12.0	●	●
YGB1135	13	480	102	150	15	2.5	11.0	●	●
YGB1200	13	430	100	148	16	2.5	10.0	●	●
YGB1305	16	350	100	142	24	2.5	9.0		●
YGB1355	20	320	90	138	28	2.5	8.0		●
YGB1405	25	240	70	130	35	2.5	8.0	●	●
YGB1605	26	170	75	118	39	3.5	5.0		●
YGB1408	26	220	/	124	38	5.0	6.5		○
YGB1475	35	70	75	105	50	4.0	5.0		●
YGB1435	30	200	65	120	38	3.0	7.0	●	○
YGB2135	20	310	100	130	28	3.0	6.0		●
YGB2185	27	160	85	125	41	4.0	4.5		●
YGB2195	28	140	80	120	45	4.5	4.5		●
YGC7105	18	270	57	142	30	8.0	1.5		○
YGC7205	20	230	55	138	32	7.5	1.5		○
YGC7705	22	160	60	130	38	8.0	1.5		○
YGC3215	26	130	70	128	40	8.0	1.0		●
YGC3205	26	125	70	120	42	8.0	1.0		○
YGC3235	27	125	55	128	38	8.0	1.0		●
YGC3305	30	85	70	110	48	7.5	1.0		●
YGC3505	24	145	115	120	37	8.0	1.5		●
YGC3105	28	105	113	113	42	7.5	1.5		○
YGDD-2	20	130	135	125	/	7.5	0.5		○
YGDD-1	22	128	132	/	40	7.0	1.0		○
YGC3208	28	150	/	118	40	8.5	1.5		●
YGC4625	45	65	45	102	48	7.0	1.0		○
YGC4725	50	28	65	/	/	7.0	1.0		●
YGC5655	50	28	65	95	55	8.0	1.0		●
YGC5665	46	40	75	100	52	8.0	1.0		●
YGC6835	45	40	75	/	/	7.0	1.0		○



仰高國際
YANGAO INTERNATIONAL

仰高國際發展有限公司

YGC616	26	180	80	118	39	3.0	5.5		●
YGC611	27	160	98	128	40	3.0	5.5		●
YGC311	23	240	102	132	38	3.0	6.0		●
YGC5800	29	80	65	110	48	7.5	1.0		○
YGC5600	24	120	65	118	43	7.5	1.0		○

Remark: The above data is based on the local representative of sampling analysis, which is only for reference, not the Goods Identification.