



Type	Particle Size (nm)	Specific Surface Area (m <sup>2</sup> /g)	DBP Absorption (cc/100g)	Tinting Strength (%)	Blackness reflectivity (%)	pH	Volatile Matter (%)
YGB1305	16	350	100	142	24	2.5	9.0
YGB1355	20	320	90	138	28	2.5	8.0
YGB1405	25	240	70	130	35	2.5	8.0
YGB1605	26	170	75	118	39	3.5	5.0
YGB1475	35	70	75	105	50	4.0	5.0
YGB1435	30	200	65	120	38	3.0	7.0
YGB2215	27	108	75	126	40	3.5	6.5
YGB2185	27	160	85	125	41	4.0	4.5
YGB2195	28	140	80	120	45	4.5	4.5
YGC3215	26	130	70	128	40	8.0	1.0
YGC3205	26	125	70	120	42	8.0	1.0
YGC3235	27	125	55	128	38	8.0	1.0
YGC3305	30	85	70	110	48	7.5	1.0
YGC3375	30	88	55	118	46	7.5	1.0
YGC3505	24	145	115	120	37	8.0	1.5
YGC4625	45	65	45	102	48	7.0	1.0
YGC4725	50	28	65	/	/	7.0	1.0
YGC611	27	160	98	128	40	3.0	5.5
YGC5800	29	80	65	110	48	7.5	1.0
YGC5600	24	120	65	118	43	7.5	1.0
YG8	30	100	90	115	44	4.0	4.0
YG110	25	125	56	125	43	8.5	1.5
YG190	30	90	56	115	49	8.5	1.5

Remark: The above data is based on the local representative of sampling analysis, which is only for reference, not the Goods Identification.