



Type	Particle Size (nm)	Specific Surface Area (m ² /g)	DBP Absorption (cc/100g)	Tinting Strength (%)	Blackness reflectivity (%)	pH	Volatile Matter (%)
YGB1305	16	350	100	142	24	2.5	9.0
YGB1355	20	320	90	138	28	2.5	8.0
YGB2215	27	108	75	126	40	3.5	6.5
YGC7105	16	270	57	142	30	8.0	1.5
YGC7205A	18	250	56	140	31	8.0	1.5
YGC7205	20	230	55	138	32	7.5	1.5
YGC7705	22	160	60	130	38	8.0	1.5
YGC3215	26	130	70	128	40	8.0	1.0
YGC3205	26	125	70	120	42	8.0	1.0
YGC3235	27	125	55	128	38	8.0	1.0
YGC3305	30	85	70	110	48	7.5	1.0
YGC3375	30	88	55	118	46	7.5	1.0
YGC3505	24	145	115	120	37	8.0	1.5
YGC3506	22	160	115	120	36	7.0	1.0
YGC3508	20	200	115	130	34	7.5	1.5
YGC3805	28	90	120	115	42	8.0	1.5
YGC3105	28	105	113	113	42	7.5	1.5
YGC4725	50	28	65	/	/	7.0	1.0
YGC6835	45	40	75	/	/	7.0	1.0
YGC5800	29	80	65	110	48	7.5	1.0
YGC5600	24	120	65	118	43	7.5	1.0
YG8	30	100	90	115	44	4.0	4.0
YG110	25	125	56	125	43	8.5	1.5
YG190	30	90	56	115	49	8.5	1.5
YG180	30	92	105	105	48	7.5	1.0
YG190M	31	90	70	115	48	8.5	1.0
YG110M	26	125	70	125	42	8.0	1.0
YG111	23	160	56	135	38	8.0	1.0

Remark: The above data is based on the local representative of sampling analysis, which is only for reference, not the Goods Identification.